



# PRODUCT REPORT<sup>®</sup>

## **AcuJoist ACJ<sup>®</sup> Series I-Joists AcuTruss Industries 1996, Ltd.**

**PR-L342**

Revised May 27, 2025

Products: AcuJoist ACJ<sup>®</sup> Series I-Joists  
AcuTruss Industries 1996 Ltd., 2003 43<sup>rd</sup> Street, Vernon, BC V1T 6K7, Canada  
(250) 545-3215  
[www.acutruss.com](http://www.acutruss.com)

1. Basis of the product report:
  - 2024 International Building Code (IBC): Sections 104.2.3 Alternative materials and 2303.1.2 Prefabricated wood I-joists
  - 2021, 2018, and 2015 International Building Code (IBC): Sections 104.11 Alternative materials and 2303.1.2 Prefabricated wood I-joists
  - 2024 International Residential Code (IRC): Sections 104.2.2 Alternative materials, and R502.1.2 and R802.1.7 Prefabricated wood I-joists
  - 2021, 2018, and 2015 International Residential Code (IRC): Sections 104.11 Alternative materials, and R502.1.2 and R802.1.8 (2021 and 2018 IRC only) Prefabricated wood I-joists
  - ASTM D5055-19e1, D5055-16, D5055-13e1, and ASTM D5055-13 recognized in the 2024 IBC and IRC, 2021 IBC and IRC, 2018 IBC and IRC, and 2015 IBC and IRC, respectively
  - APA PRI-400 Performance Standard for Residential I-Joists
  - APA PRI-405 Performance Standard for Commercial I-Joists
  - 2021 and 2015 ANSI/AWC Special Design Provisions for Wind and Seismic (SPDWS) recognized in the 2024 and 2021 IBC, 2018 and 2015 IBC, respectively
  - 2024, 2018, and 2015 ANSI/AWC NDS, National Design Specification for Wood Construction recognized in the 2024 IBC and IRC, 2021 and 2018 IBC and IRC, and 2015 IBC and IRC, respectively
  - APA Reports T2021P-23, T2022P-14, T2023P-25, and T2025P-09, and other qualification data
2. Product description:

AcuJoist ACJ<sup>®</sup> I-joists are described in Table 1 in accordance with the in-plant manufacturing standard approved by APA.
3. Design properties:

Tables 2 and 3 list the allowable design properties for the AcuJoist ACJ I-joists covered by this report. The allowable spans for AcuJoist ACJ I-joists qualified as the PRI series shall be permitted in accordance with the APA *Performance Rated I-Joists*, Form Z725, and APA *PRI-405 Performance Standard for Commercial I-Joists* ([www.apawood.org/resource-library](http://www.apawood.org/resource-library)).
4. Product installation:

AcuJoist ACJ I-joists covered by this report shall be installed in accordance with the recommendations provided by the manufacturer (see link above) or the APA *Performance Rated I-Joists*, Form Z725 (see link above) for products qualified as the PRI Series. Permissible web holes and cantilever reinforcements shall be in accordance with the recommendations provided by the manufacturer or with the APA Z725 for products qualified as the PRI Series.

5. Fire-rated assemblies:  
Fire-rated assemblies shall be constructed in accordance with the recommendations provided by the manufacturer or APA *Fire-Rated Systems*, Form W305 (see link above) for products qualified as the PRI Series.
6. Limitations:
  - a) AcuJoist ACJ I-joists shall be designed in accordance with the applicable code and the National Design Specification for Wood Construction using the allowable design properties specified in this report.
  - b) AcuJoist ACJ I-joists are limited to dry service conditions where the average equilibrium moisture content of solid-sawn lumber is less than 16%.
  - c) AcuJoist ACJ I-joists are produced in Kelowna, BC, Canada under a quality assurance program audited by APA.
  - d) This report is subject to re-examination in one year.
7. Identification:  
The AcuJoist ACJ I-joists described in this report are identified by a label bearing the manufacturer's name (AcuTruss Industries 1996, Ltd.) and/or trademark, the APA assigned plant number 1138, the I-joist series designation and depth, the APA logo, the report number PR-L342, and a means of identifying the date of manufacture.

Table 1. Description of AcuJoist ACJ I-Joists<sup>(a)</sup>

I-Joist Series	Also Qualified for	I-Joist Depths (in.)	Flanges				Web	
			Material	G	Dimension		Material	Thickness (in.)
					Depth (in.)	Width (in.)		
ACJ-40	PRI-40	9-1/2 – 16	Proprietary SPF	0.42	1-1/2	2-1/2	OSB	3/8
ACJ-60	PRI-60	9-1/2 - 16	MSR SPF	0.46	1-1/2	2-1/2	OSB	3/8
ACJ-80	PRI-80	11-7/8 - 16	MSR SPF	0.46	1-1/2	3-1/2	OSB	3/8
	C1	18						

<sup>a)</sup> Referenced dimensions are nominal. Tolerances are as specified in the in-plant quality manual.

Table 2. Design Properties (Allowable Stress Design) for AcuJoist ACJ I-Joists<sup>(a,b)</sup>

I-Joist Depth (in.)	I-Joist Series	EI <sup>(c)</sup> (10 <sup>6</sup> lbf-in. <sup>2</sup> )	M <sup>(d)</sup> (lbf-ft)	V <sup>(e)</sup> (lbf)	VLC <sup>(f)</sup> (lbf/ft)	K <sup>(g)</sup> (10 <sup>6</sup> lbf)
9-1/2	ACJ-40	184	2,735	1,120	2,000	4.94
	ACJ-60	219	3,780	1,120	2,000	4.94
11-7/8	ACJ-40	313	3,545	1,420	2,000	6.18
	ACJ-60	371	4,900	1,420	2,000	6.18
	ACJ-80	518	6,940	1,420	2,000	6.18
14	ACJ-40	459	4,370	1,710	2,000	7.28
	ACJ-60	544	5,895	1,710	2,000	7.28
	ACJ-80	756	8,360	1,710	2,000	7.28
16	ACJ-40	625	5,070	1,970	2,000	8.32
	ACJ-60	739	6,835	1,970	2,000	8.32
	ACJ-80	1,024	9,690	1,970	2,000	8.32
18	ACJ-80	1,329	10,900	2,500	1,750	11.52

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N.

- <sup>(a)</sup> The tabulated values are design values for the normal duration of load. All values, except for EI, VLC, and K, shall be adjusted for other load durations in accordance with the code.
- <sup>(b)</sup> Referenced design values must be adjusted, as applicable, in accordance with section 7.3 of the NDS.
- <sup>(c)</sup> Bending stiffness (EI) of the I-joist.
- <sup>(d)</sup> Moment capacity (M) of the I-joist, which shall not be increased by any repetitive member factor.
- <sup>(e)</sup> Shear capacity (V) of the I-joist.
- <sup>(f)</sup> Uniform vertical load capacity of the I-joist.
- <sup>(g)</sup> Coefficient of shear deflection (K). For calculating the uniform load and center-point load deflections of the I-joist in a simple-span application, use Eqs. 1 and 2.

$$\text{Uniform Load: } \delta = \frac{5 \omega L^4}{384 EI} + \frac{\omega L^2}{K} \quad [1]$$

$$\text{Center-Point Load: } \delta = \frac{PL^3}{48 EI} + \frac{2PL}{K} \quad [2]$$

where  $\delta$  = calculated deflection (in.),  $\omega$  = uniform load (lbf/in.),  
 $P$  = concentrated load (lbf),  $L$  = design span (in.),  
 $EI$  = bending stiffness of the I-joist (lbf-in.<sup>2</sup>), and  $K$  = coefficient of shear deflection (lbf-ft/in.).

Table 3. Reaction Capacities (Allowable Stress Design) for AcuJoist ACJ I-Joists<sup>(a,b)</sup>

I-Joist Depth (in.)	I-Joist Series	Intermediate Reaction (lbf)	End Reaction <sup>(b)</sup> (lbf)			
		3-1/2 in. Brg. Length	1-3/4 in. Brg. Length		4 in. Brg. Length	
		Without Brg. Stiffeners	With Brg. Stiffeners		With Brg. Stiffeners	
			No	Yes	No	Yes
9-1/2	ACJ-40	2,160	1,080	1,080	1,120	1,120
	ACJ-60	2,160	1,080	1,080	1,120	1,120
11-7/8	ACJ-40	2,500	1,200	1,200	1,420	1,420
	ACJ-60	2,500	1,200	1,200	1,420	1,420
	ACJ-80	2,760	1,280	1,280	1,420	1,420
14	ACJ-40	2,500	1,200	1,200	1,550	1,710
	ACJ-60	2,500	1,200	1,200	1,550	1,710
	ACJ-80	3,020	1,280	1,280	1,550	1,710
16	ACJ-40	2,500	1,200	1,200	1,550	1,970
	ACJ-60	2,500	1,200	1,200	1,550	1,970
	ACJ-80	3,020	1,280	1,280	1,550	1,970
18	ACJ-80	3,355	1,400	2,035	1,625	2,395

For SI: 1 inch = 25.4 mm, 1 foot = 304.8 mm, 1 lbf = 4.448 N, 1 psi = 6.895 kPa.

- (a) The tabulated values are design values for the normal duration of load. All values shall be permitted to be adjusted for other load durations provided that the adjusted reaction design value is not greater than the value specified below. Bearing stiffeners shall be installed in accordance with the recommendations provided by the manufacturer and APA Z725.
- (b) Referenced design values must be adjusted, as applicable, in accordance with section 7.3 of the NDS.

I-Joist Depth	I-Joist Series	Maximum adjusted reaction capacity <sup>(c,d)</sup> (lbf)					
		1-3/4 in. Brg. Length		3-1/2 in. Brg. Length		4 in. Brg. Length	
		Brg. Stiffeners		Brg. Stiffeners		Brg. Stiffeners	
		No	Yes	No	Yes	No	Yes
All	ACJ-40	1,750		3,495		3,995	
	ACJ-60	2,160		4,320		4,935	
	ACJ-80	3,080		6,155		7,035	

- (c) Interpolation between bearing lengths is permitted.
- (d) The maximum adjusted reaction capacity shall not be adjusted for load duration.

APA – *The Engineered Wood Association* is an approved national standards developer accredited by American National Standards Institute (ANSI). APA publishes ANSI standards and Voluntary Product Standards for wood structural panels and engineered wood products. APA is an accredited certification body under ISO/IEC 17065 by Standards Council of Canada (SCC), an accredited inspection agency under ISO/IEC 17020 by ANSI National Accreditation Board (ANAB), and an accredited testing organization under ISO/IEC 17025 by ANAB. APA is also an approved Product Certification Agency, Testing Laboratory, Quality Assurance Entity, Validation Entity, and Product Evaluation Entity by the State of Florida, and an approved testing laboratory by City of Los Angeles.

**APA – THE ENGINEERED WOOD ASSOCIATION  
HEADQUARTERS**

7011 So. 19<sup>th</sup> St. ▪ Tacoma, Washington 98466  
Phone: (253) 565-6600 ▪ Fax: (253) 565-7265 ▪ Internet Address: [www.apawood.org](http://www.apawood.org)

**PRODUCT SUPPORT HELP DESK**  
(253) 620-7400 ▪ E-mail Address: [help@apawood.org](mailto:help@apawood.org)

**DISCLAIMER**

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. No warranties, express or implied, including as to fitness for a particular purpose, are made regarding this report. Neither APA, nor its members shall be liable, or assume any legal liability or responsibility, for damages, direct or indirect, arising from the use, application of, and/or reference to opinions, findings, conclusions or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility for product performance or designs as actually constructed.